



926 | BASE OPACA_ PASTELLO

BASE COAT MATT _ PASTEL
BASES MULTICRYL 900 + BINDER 900.DS26

PREPARAZIONE

Preparation | Préparation |
Preparación | Vorbereitung



RAPPORTO MISCELA

Mixing ratio | Rapport de mélange |
Relación de Mezcla | Mischungsverhältnis

100 : 10 : 70

PRODOTTO

Product | Produit | Producto | Produkt

926

100 VOL

CATALIZZATORE

Hardener | Catalyseur | Catalizador | Katalysator

993.MS--

10 VOL

DILUENTE

Thinner | Diluant | Diluyente | Verdünner

075.0020 STANDARD
075.0015 FAST
075.0030 SLOW

70 VOL

FILTRO

Filter | Filtre | Filtro | Filter

2500 Maglie | Meshes | Mailles | Mallas | Poren (125µ)

Exclusively for uses not regulated by Legislative Decree No. 161/2006 and European Norm 2004/42

TDS D19M ED. 07/2020

APPLICAZIONE

Application | Application |
Aplicación | Anwendung

	POT Pot life (20° C) Vie en pot (20° C) Vida de la mezcla (20 °C) Topfzeit (20° C)	-
	VISCOSITÀ APPLICAZIONE Application viscosity Viscosité d'application Viscosidad de aplicación Spritzviskosität	16" ±1" DIN/4
	REGOLAZIONE DELLA PISTOLA Airbrush adjustment Regulación de la pistola Réglage du pistolet Sprühpistoleneinstellung	2 Giri Turns Tours Vueltas Umdrehunge
	UGELLO Nozzle Buse Boquilla Düse	1,2-1,3 RP
	PRESSIONE ARIA Air Pressure Pression de l'air Presión de aplicación Luft	1,8-2 RP
	NUMERO MANI Number of coats Nombre des couches Numero de capas Anzahl Spritzgänge	2
	INTERVALLO TRA LE MANI Time interval between coats Intervalle entre les couches Intervalo entre capas Intervall zwischen den Spritzgängen	15' 20' - 20° 25°C Ventilazione Air drying Ventilation Ventilación Im Luftstrom

ESSICCAZIONE & RESA

Drying & Yield | Séchage & Rendement |
Secado & Rendimiento | Trocknung &
Ergiebigkeit

	APPASSIMENTO Flash time Tiempo de secado Flétrissement Abluftzeit	15' 20' - 20° 25°C Ventilazione Air drying Ventilation Ventilación Im Luftstrom
	ESSICCAZIONE COMPLETA Through drying Séchage complet secado completo vollständige Trocknung	20 °C: - 60 °C: -
	SPESSORE FILM SECCO Dry film thickness Espesor de película seca Épaisseur de la pellicule sèche Trockenschichtstärke	25 ± 5 μ
	RESA RFU - m² / kg x 1 μ Yield RFU Rendement RFU Rendimiento RFU Ergiebigkeit RFU	300

CARTEGGIATURA

Sanding | Ponçage
Lijado | Schmirgeln

	ROTO ORBITALE SECCO Roto-orbital dry sanding Orbital à sec Roto-orbital seco Exzenterschleifer Trocken	P600-P800 Vecchia Verniciatura Old Paint Coat Peinture Existante Antiquo pintado Alter Lackierung P500-P600 Fondo Filler Apprêt Aparejo Grundierung
	ROTO ORBITALE BAGNATO Roto-orbital wet sanding Orbital humide Roto-orbital mojado Exzenterschleifer Nass	-
	CART MANUALE BAGNATO Manual sanding on wet ponçage manuel humide lijado manual en húmedo manuelles schmirgeln auf feuchtem grund	-
	CART MANUALE SECCO Dry manual sanding Ponçage manuel à sec Lijado manual a seco Handschliff Trocken	P500-P600 Vecchia Verniciatura Old Paint Coat Peinture Existante Antiquo pintado Alter Lackierung P400-P500 Fondo Filler Apprêt Aparejo Grundierung
	SOVRAVERNICIABILE Overcoatable Survernissable Repintable Überstreichbar	Dopo After Depuis Después Nach 15'-20' 20°C

PRODOTTI COMPLEMENTARI

| Complementary products | Produits complémentaires | Productos complementarios | Komplementäres Produkt

	CATALIZZATORE Hardener Catalyseur Catalizador Katalysator	DILUENTE Thinner Diluant Diluyente Verdünner	AUSILIARI Auxiliaries Auxiliaires Auxiliares Hilfsmittel
993.MS--	Standard Maxi solid		
075.0020		Standard	
075.0015		Rapido Fast Rapide Rápido Schnell	
075.0030		Lento Slow Lent Lento Langsam	
074.DS--			Per sfumature For fade out Pour raccords fondus Para difuminados Für Abtönungen

CONSERVABILITA'

Storing | Durée de conservation | Tiempo de conservación | Haltbarkeit

	CONSERVABILITA' Storing Durée de conservation Tiempo de conservación Haltbarkeit	24 Mesi Months Mois Meses Monate 5 < °C < 35
---	--	---



926 | BASE OPACA_ PASTELLO

BASE COAT MATT _ PASTEL

BASES MULTICRYL 900 + BINDER 900.DS26

DESCRIPTION

Class 926 of the Multicryl 900 series allows reproducing double layer pastel colours, matrices and variants, of the cars and motorcycles of the world through bases with a high pigment concentration and the 900 DS26 binding agent. Color codes used in industrial bodywork and ACE (Agriculture, Construction, Earthmoving) sectors are also available.

PRODUCT FEATURES - BENEFITS

- Very high yield: exceptional covering yield in the standard version, unparalleled in the High Solid version.
- Colorimetric capacity: colour point accuracy and wide range of the available formulations in the DataBase
- Easy application and fast drying
- Reproducibility over time: maximum base stability

DIRECTIONS FOR USE

PREPARATION:

- Use bases regularly mixed (after first opening)
- Each color formulation is available in the PalcolorFinder
- Filter the diluted product with a 2500- mesh filter (125µ)
- To avoid thermoplasticity phenomena, thin layers (20-30µ) must be applied. Given the complexity of reproducing these thicknesses accurately, it is recommended to always catalyse the 926 base at 10% with 993MS---

APPLICATION:

- Filler: For each colour, the recommended filler colour is reported in the Palcolorfinder.
- The 926 colour must be applied on a well-dry and sanded filler:
 - o **1 light and very thin coat**
The distance from the substrate must be 20 cm, air pressure at the gun butt must be 3-4 bar when using a standard gun or 1.8 - 2.2 bar if using an HLVP-LVLP gun. Nozzle 1.2 - 1.3 mm
This stage is optional but highly recommended to remove any micro-impurities due to the presence of silicone in the air.
 - o **2 standard coats**
After the flash-time of 15 - 20 minutes at 20°C, the 926 matt base must be dry.
 - o After 15-20 minutes of drying time at 20°C apply the VOC 420 gr|lt series 223 solvent-based, 923.AS90 scratch-proof or 123.0250 water-based clear coat.

Exclusively for uses not regulated by Legislative Decree No. 161/2006 and by European Regulation No. 2004/42.

TDS D19M ED. 07/2020

TABLE A.1.
AIRBRUSH ADJUSTMENT

GUN MODEL	SATA RP 4000/5000/55 00	WALCOM HTE	IWATA WB400	IWATA WBX400	DE VILBISS GT PRO T1 TRANS- TECH	DE VILBISS GT PRO H1 HVLP	ANI IDEA
NOZZLE	1.2-1.3 MM	1.2 MM	1.3 MM	1.2-1.3 MM	1.3	1.3	WB
PRESSURE IN BAR, MEASURED AT GUN BUTT	1.8 – 2.2 Bar	2.2 – 2.5 Bar	2 Bar	1.8 – 2 Bar	1.8 – 2 Bar	1 – 1.2 Bar	2.5 Bar
FAN-SHAPED OPENING	ALL OPEN	ALL OPEN	ALL OPEN	ALL OPEN	ALL OPEN	ALL OPEN	ALL OPEN
PRODUCT DISPENSING ADJUSTMENT (PRODUCT DISPENSER RPM)*	MIN 1.1/4 -2 MAX	MIN. 2 -2.3/4 MAX.	MIN 2.1/4 -3 MAX	MIN.1.3/4 -2.5 MAX.	MIN 1.1/2 -2.5 MAX	MIN 1.1/2 -2.1/4 MAX	MIN 2.1/4 -3 MAX
DISTANCE FROM THE OBJECT	10-15 CM	10-15 CM	10-15 CM	10-15 CM	10-15 CM	10-15 CM	10-15 CM

* the lower speed must be used for low-viscosity colours

TOOL WASHING

Use washing thinner code 044----- or nitro thinner code 047-----.

PRODOTTI PER USO PROFESSIONALE

I dati forniti in questa scheda sono il frutto della nostra migliore esperienza. Tuttavia devono essere considerati quali informazioni senza alcun valore vincolante, anche per quanto riguarda eventuali diritti di proprietà di terzi, e non esime il cliente da eseguire propri controlli dei prodotti da noi forniti allo scopo di stimare l'idoneità o meno ai procedimenti ed ai cicli da lui previsti. L'applicazione e l'impiego dei prodotti (oltre al tipo di supporto, condizioni di essiccazione, etc.) avvengono fuori dalle nostre possibilità di controllo e ricadono pertanto sotto l'esclusiva responsabilità del cliente. Ci riserviamo, senza obbligo di preavviso, di modificare | aggiornare periodicamente le informazioni contenute nella scheda : l'ultima versione sostituisce ogni versione precedente. È responsabilità dell'utilizzatore verificare che la scheda sia aggiornata prima di utilizzare il prodotto. Le informazioni in materia di salute e sicurezza sono riportate nella Scheda di Sicurezza.

PRODUCTS FOR PROFESSIONAL USE

The data provided on this data sheet represent a summary of our best experience. However, it must be deemed merely informational in nature, without any binding value, also with regard to the possible property rights of third parties, and does not exempt the clients from carrying out their own verifications on the products we supply for the purpose of assessing their suitability for the processes and cycles to be implemented by the clients. The application and use of the products (in addition to the type of substrate, drying conditions etc.) are beyond our control and therefore fall under the exclusive responsibility of the client. We reserve the right to periodically change and update without prior advance notice the information contained in the sheet: the latest version replaces the previous one. It is the responsibility of the user to verify that the data sheet is the most updated version before using the product. The information regarding health and safety is reported in the Safety Sheet.

PRODUITS À USAGE PROFESSIONNEL

Les données fournies dans cette fiche sont le résultat de notre meilleure expérience. Elles doivent toutefois être considérées comme des informations sans valeur contraignante, également en ce qui concerne les éventuels droits de propriété de tiers, et elles ne dispensent pas le client d'effectuer ses propres contrôles des produits fournis dans le but d'estimer la conformité ou non des procédés et des cycles prévus. L'application et l'utilisation des produits (autre le type de support, les conditions de séchage, etc.) échappent à notre contrôle et relèvent donc de la responsabilité exclusive du client. Nous nous réservons le droit, sans préavis, de modifier | mettre à jour périodiquement les informations contenues dans la fiche : la dernière version remplace toute version antérieure. L'utilisateur a la responsabilité de vérifier que la fiche a été mise à jour avant d'utiliser le produit. Les informations relatives à la santé et à la sécurité se trouvent dans les Fiches de Données de Sécurité.

PRODUCTOS PARA USO PROFESIONAL

Los datos indicados en esta ficha son el resultado de nuestra mejor experiencia. Sin embargo, debe considerarse información sin ningún valor vinculante, también en lo que respecta a los posibles derechos de propiedad de terceros, y no exime al cliente de efectuar sus propios controles sobre los productos suministrados con el fin de evaluar la idoneidad de los procedimientos y ciclos previstos. La aplicación y el uso de los productos (además del tipo de soporte, condiciones de secado, etc.) se efectúan fuera de nuestra posibilidad de control y, por lo tanto, bajo exclusiva responsabilidad del cliente. Nos reservamos, sin obligación de aviso previo, el derecho de modificar | actualizar periódicamente la información indicada en la ficha. La última versión sustituye cualquier versión anterior. Es responsabilidad del usuario comprobar si la ficha está actualizada antes de utilizar el producto. La información en materia de salud y seguridad se indica en las fichas de seguridad.

PRODUKTE FÜR DEN PROFESSIONELLEN EINSATZ

Die auf diesem Datenblatt angegebenen Daten drücken unsere Erfahrungen mit dem Produkt aus. Sie verstehen sich jedoch als unverbindliche Informationen, auch in Bezug auf eventuell vorhandene dritte Schutzrechte, und befreit den Kunden daher nicht, die von uns gelieferten Produkte kundenseitig zu testen, um ihre Eignung hinsichtlich der kundenseitig benutzten Verfahren und Zyklen zu bestätigen oder zu verneinen. Die Anwendung und der Einsatz der Produkte (Art des Untergrunds, Trocknungsbedingungen usw.) entziehen sich unserer Kontrolle und liegen daher in alleiniger Kundenverantwortung. Wir behalten uns das Recht vor, die im Datenblatt angeführten Informationen ohne vorherige Ankündigung periodisch zu verändern/zu aktualisieren, wobei neuere Ausgaben frühere Ausgaben ersetzen. Es obliegt dem Nutzer vor einer Verwendung des Produkts zu prüfen, ob das Datenblatt aktualisiert wurde. Informationen in Bezug auf Gesundheit und Sicherheit enthält das Sicherheitsdatenblatt.